

JC10 REC 3 FEB 2002

FORM PTO-1390 (REV. 11-2000)		U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE		ATTORNEY'S DOCKET NUMBER 3787-0111P	
TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371				U.S. APPLICATION NO. (If known, see 37 CFR 1.5) 10/069407	
INTERNATIONAL APPLICATION NO. PCT/SE00/01649		INTERNATIONAL FILING DATE August 28, 2000		PRIORITY DATE CLAIMED August 26, 1999	
TITLE OF INVENTION A METHOD OF PRODUCING A PLASTIC PRODUCT AND AN ARRANGEMENT FOR MOULDING PLASTIC PRODUCTS UTILISED THEREFOR					
APPLICANT(S) FOR DO/EO/US OHMAN, Per Ove; LUNDBLADH, Lars Rune					
Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:					
1. <input checked="" type="checkbox"/> This is a FIRST submission of items concerning a filing under 35 U.S.C. 371. 2. <input type="checkbox"/> This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371. 3. <input checked="" type="checkbox"/> This express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39 (1). 4. <input checked="" type="checkbox"/> The US has been elected by the expiration of 19 months from the priority date (Article 31). 5. <input checked="" type="checkbox"/> A copy of the International Application as filed (35 U.S.C. 371(c)(2)) a. <input checked="" type="checkbox"/> is transmitted herewith (required only if not transmitted by the International Bureau). (WO 01/14116 A1) b. <input type="checkbox"/> has been transmitted by the International Bureau. c. <input type="checkbox"/> is not required, as the application was filed in the United States Receiving Office (RO/US). 6. <input checked="" type="checkbox"/> An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)). a. <input checked="" type="checkbox"/> is transmitted herewith. b. <input type="checkbox"/> has been previously submitted under 35 U.S.C. 154(d)(4) 7. <input checked="" type="checkbox"/> Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3)). a. <input type="checkbox"/> are transmitted herewith (required only if not transmitted by the International Bureau). b. <input type="checkbox"/> have been transmitted by the International Bureau. c. <input type="checkbox"/> have not been made; however, the time limit for making such amendments has NOT expired. d. <input checked="" type="checkbox"/> have not been made and will not be made. 8. <input type="checkbox"/> An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)). 9. <input checked="" type="checkbox"/> An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)). 10. <input type="checkbox"/> An English language translation of the annexes of the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).					
Items 11. to 20. below concern document(s) or information included:					
11. <input checked="" type="checkbox"/> An Information Disclosure Statement under 37 CFR 1.97 and 1.98, Form PTO-1449(s), and International Search Report (PCT/ISA/210) with 5 cited document(s). 12. <input checked="" type="checkbox"/> An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included. 13. <input checked="" type="checkbox"/> A FIRST preliminary amendment. 14. <input type="checkbox"/> A SECOND or SUBSEQUENT preliminary amendment. 15. <input type="checkbox"/> A substitute specification. 16. <input type="checkbox"/> A change of power of attorney and/or address letter. 17. <input type="checkbox"/> A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821-1.825. 18. <input type="checkbox"/> A second copy of the published international application under 35 U.S.C. 154(d)(4). 19. <input type="checkbox"/> A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4). 20. <input checked="" type="checkbox"/> Other items or information: 1.) International Preliminary Examination Report (PCT/IPEA/409) 2.) Eight (8) Sheets of Formal Drawings					

U.S. APPLICATION NO (if known, see 37 CFR 1.5) 10/069407		INTERNATIONAL APPLICATION NO PCT/SE00/01649		ATTORNEY'S DOCKET NUMBER 3787-0111P	
--	--	--	--	--	--

<p>21. <input checked="" type="checkbox"/> The following fees are submitted:</p> <p>BASIC NATIONAL FEE (37 CFR 1.492(a)(1)-(5): Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO. \$1,040.00</p> <p>International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO \$890.00</p> <p>International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO. \$740.00</p> <p>International preliminary examination fee (37 CFR 1.482) paid to USPTO but all claims did not satisfy provisions of PCT Article 33(1)-(4) \$710.00</p> <p>International preliminary examination fee (37 CFR 1.482) paid to USPTO and all claims satisfied provisions of PCT Article 33(1)-(4) \$100.00</p> <p>ENTER APPROPRIATE BASIC FEE AMOUNT =</p> <p>Surcharge of \$130.00 for furnishing the oath or declaration later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(e)).</p> <table border="1" style="width:100%; border-collapse: collapse;"> <tr> <th style="width:20%;">CLAIMS</th> <th style="width:20%;">NUMBER FILED</th> <th style="width:20%;">NUMBER EXTRA</th> <th style="width:20%;">RATE</th> <th style="width:20%;"></th> </tr> <tr> <td>Total Claims</td> <td>33 - 20 =</td> <td>13</td> <td>X \$18.00</td> <td>\$ 234.00</td> </tr> <tr> <td>Independent Claims</td> <td>2 - 3 =</td> <td>0</td> <td>X \$84.00</td> <td>\$ 0.00</td> </tr> <tr> <td colspan="4">MULTIPLE DEPENDENT CLAIM(S) (if applicable) Yes</td> <td>+ \$280.00</td> </tr> <tr> <td colspan="4">TOTAL OF ABOVE CALCULATIONS =</td> <td>\$ 1,554.00</td> </tr> </table> <p><input type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27. The fees indicated above are reduced by 1/2.</p> <p style="text-align: right;">SUBTOTAL = \$ 1,554.00</p> <p>Processing fee of \$130.00 for furnishing the English translation later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(f)).</p> <p style="text-align: right;">TOTAL NATIONAL FEE = \$ 1,554.00</p> <p>Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property +</p> <p style="text-align: right;">TOTAL FEES ENCLOSED = \$ 1,594.00</p> <table border="1" style="width:100%; border-collapse: collapse;"> <tr> <td style="width:60%;"></td> <td style="width:20%; text-align: right;">Amount to be:</td> <td style="width:20%;"></td> </tr> <tr> <td></td> <td style="text-align: right;">refunded</td> <td>\$</td> </tr> <tr> <td></td> <td style="text-align: right;">charged</td> <td>\$</td> </tr> </table>	CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE		Total Claims	33 - 20 =	13	X \$18.00	\$ 234.00	Independent Claims	2 - 3 =	0	X \$84.00	\$ 0.00	MULTIPLE DEPENDENT CLAIM(S) (if applicable) Yes				+ \$280.00	TOTAL OF ABOVE CALCULATIONS =				\$ 1,554.00		Amount to be:			refunded	\$		charged	\$	
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE																																
Total Claims	33 - 20 =	13	X \$18.00	\$ 234.00																															
Independent Claims	2 - 3 =	0	X \$84.00	\$ 0.00																															
MULTIPLE DEPENDENT CLAIM(S) (if applicable) Yes				+ \$280.00																															
TOTAL OF ABOVE CALCULATIONS =				\$ 1,554.00																															
	Amount to be:																																		
	refunded	\$																																	
	charged	\$																																	

a. ☒ A check in the amount of \$ **1,594.00** to cover the above fees is enclosed.


b. ☐ Please charge my Deposit Account. No. _____ in the amount of \$ _____ to cover the above fees.
A duplicate copy of this sheet is enclosed.

c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any
overpayment to Deposit Account No. 02-2448.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.

Send all correspondence to:
Birch, Stewart, Kolasch & Birch, LLP or Customer No. 2292
P.O. Box 747
Falls Church, VA 22040-0747
(703) 205-8000

Date: February 26, 2002

By 
Gerald M. Murphy, Jr., #28,977

/rem

107 007-707
JC13 Rec'd PCT/PTO 26 FEB 2002
PATENT
3787-0111P

IN THE U.S. PATENT AND TRADEMARK OFFICE

Applicant: OHMAN, Per Ove et al.
Int'l. Appl. No.: PCT/SE00/01649
Appl. No.: New Group:
Filed: February 26, 2002 Examiner:
For: A METHOD OF PRODUCING A PLASTIC
PRODUCT AND AN ARRANGEMENT FOR
MOULDING PLASTIC PRODUCTS UTILISED
THEREFOR

PRELIMINARY AMENDMENT

BOX PATENT APPLICATION

Assistant Commissioner for Patents
Washington, DC 20231

February 26, 2002

Sir:


The following Preliminary Amendments and Remarks are respectfully submitted in connection with the above-identified application.

AMENDMENTS

IN THE SPECIFICATION:

Please amend the specification as follows:

Before line 1, insert --This application is the national phase under 35 U.S.C. § 371 of PCT International Application No. PCT/SE00/01649 which has an International filing date of August 28, 2000, which designated the United States of America.--



Docket No. 3787-0111P

REMARKS

The specification has been amended to provide a cross-reference to the previously filed International Application.


Entry of the above amendments is earnestly solicited. An early and favorable first action on the merits is earnestly solicited.

If necessary, the Commissioner is hereby authorized in this, concurrent, and future replies, to charge payment or credit any overpayment to Deposit Account No. 02-2448 for any additional fees required under 37 C.F.R. § 1.16 or under 37 C.F.R. § 1.17; particularly, extension of time fees.

Respectfully submitted,

BIRCH, STEWART, KOLASCH & BIRCH, LLP

By



Gerald M. Murphy Jr., #28,977

GMM/rem
3787-0111P

P.O. Box 747
Falls Church, VA 22040-0747
(703) 205-8000

(Rev. 11/13/01)

A METHOD OF PRODUCING A PLASTIC PRODUCT AND AN ARRANGEMENT FOR MOULDING PLASTIC PRODUCTS UTILISED THEREFOR

Technical field

5 The present invention relates primarily to a method of producing a plastic product having at least one outer surface assigned a microstructure, utilising an arrangement for moulding plastic products.

 This arrangement for producing plastic products has at least two mould parts movable towards and away from each other, a predetermined volume or
10 quantity of a viscous polymerisable plastic material being supplied to a first cavity formed between the mould parts.

 By the expression "polymerisable plastic material" is meant a plastic material having a viscosity equivalent to that of water or thinly fluid syrup.

 The method in accordance with the invention is designed for use in both
15 die-casting and compression moulding.

 In the case of die-casting the mould parts assume a co-operating position in relation to each other and a cavity formed between the mould parts has a shape conforming to an outer shape of the plastic product, viscous plastic material being pressed into the cavity and being permitted to polymerise there.

20 In the case of compression moulding the mould parts shall be able to assume an almost fully united position in order to allow a predetermined volume or quantity of a viscous polymerisable plastic material to be supplied to a first cavity formed between the mould parts.

 The method in accordance with the invention is thus based on the mould
25 parts being subsequently compressed to a fully united position and said viscous plastic material being distributed under a positive pressure within a smaller second cavity corresponding to the shape of the final plastic product, the outer form of which will conform to the internal shape of the second cavity formed by the mould parts.

30 The defining inner surfaces of the second cavity will thus correspond to the outer defining surfaces for the final product. However, each microstructured surface portion of the final product will have its corresponding microstructured surface portion in the second cavity.

Although the invention may be applied in the die-casting technology the significant properties of the invention will be illustrated in the following in the compression moulding technology, utilising a viscous polymerisable plastic material.

Background art

Various methods have been proposed for producing a plastic product with microstructured surface portions, utilising an arrangement for producing plastic products.

5 Considering the application so significant for the present invention, namely the prime object of providing a method and an arrangement for producing plastic products for the manufacture of plastic discs containing information, such as CD discs, DVD discs or, in a wider application, micromechanical discs of various types, a plurality of methods and arrangements are known.

10 Microfluids fall within the latter application, where a fluid shall pass through channels in the disc formed by means of micromechanics, for measuring various entities. Open channels in the surface may here be covered by a lid in order to form closed channels in the surface.

15 A more specific application is to allow winding channels to be formed on a disc in order to separate different DNA molecules with electrophoresis. A voltage forces the molecules forward and an optical detector registers when they arrive.

 The microstructure of CD discs and storage of information currently has a height of 0.1 μm and a breadth (elevation and depression) of 0.7 μm .

20 The microstructure useful in microfluids for flow handling and optics may have a height of 10-100 μm and a channel breadth of 20-100 μm .

 For information storage it is known to produce CD discs with high or extremely high storage capacity.

25 In this context it should be mentioned that CD discs of the type under discussion have been given various designations for the relevant storage capacity, such as DVD5, DVD8 (Digital Versatile Disc), where the figure stated indicates the storage capacity in Gbyte.

30 An arrangement for producing plastic products which is currently extremely useful for producing such CD discs is the use of an injection moulding machine for thermoplastics where two mould parts used shall assume a position fully co-operating with each other and where the mould parts form said second cavity.

 In this co-operating position a heated thermoplastic compound, in the form of a plastic composite, is pressed through a fixed mould part to a space or a second cavity formed between the two mould parts, for die-casting of a flat plastic component with microstructured surface portions.

The movable mould part is then moved away from the fixed mould part and the formed flat moulded plastic component or the CD disc is removed from the movable mould part.

In this application curing of the thermoplastic material occurs through a
5 considerable drop in temperature, usually in the order of 100°C. The drop in temperature stated here applies to the difference between the temperature of the feeding screw and of the plastic product upon removal from the mould parts.

The ambition to maintain a high rate of manufacture demands a temperature in the mould parts and the second cavity that has a cooling and curing effect
10 on the thermoplastic material supplied, with reduction of the replication ability as regards the microstructured surface section.

However, the present invention is also based on an, albeit, previously known method of producing a plastic product and an arrangement for producing plastic products which, as a result of the thermoplastic-based manufacturing
15 method described has been pushed aside since, with current technology and demands, it has been considered too expensive and too slow. This method with an arrangement for producing plastic products has therefore only be used to a limited extent for producing genuine, complete plastic products with one or more microstructured surfaces.

20 The method and the arrangement for producing plastic products from which the present invention can be deemed to emanate are shown and described in more detail in the publication "High Density CD and Industrial approach", publication number ISBM 90-80 2001-2-3, particularly pages 77-79.

The method and arrangement for producing plastic products from which
25 the present invention has been developed are described in more detail with reference to the following Figures 1 and 2.

The advantage with this method and the associated arrangement for producing plastic products is that the replication capacity is good, thanks to a polymerisation of the plastic material, in that a viscous plastic material can be pressed
30 out into a second space and is only thereafter activated so that polymerisation occurs.

Additional examples of the state of the prior art are shown and described in the following patent publications:

EP-A1-0 628 957

Here is shown and described an arrangement for injection moulding of optical recording blanks comprising two mould parts, moveable towards each other, which are designed and displaceable in order to form a cavity between them, corresponding to the shape of the recording blank.

Referring now to Figure 6, the arrangement is shown in cross-section and from this figure it can be seen that a polycarbonate-based plastic shall be pressed in a moulding apparatus based on the principle of injection.

The moulding process, for the manufacturing of an optical disc substrate, is based upon that an outer edge (21a) for the movable mould part (21) shall be brought into contact with the upper surface (28a) for the mould support (28) and which is arranged at the periphery of the lateral side part (22) of the cavity in order to close the mould.

In this position, the plastic material is injected from the orifice (27) and the nozzle (13) and into the space (20). During this injection process, the space is opened by the moveable part (21) being displaced from this space according to Figure 7, and subsequently the parts are pressed together again towards the position shown in Figure 6, according to Figure 8.

It should especially be noted that the finished product will here comprise of an entire disc, (the central part of which does not display a hole) the central portion of which however is formed with a thinner area (of the part 24) and to this area is integrally attached a funnel-shaped part, cured by cooling and having the shape of a truncated cone, which must be regarded as a residual product.

The thinner portion and the funnel-shaped part shall be separated through punching, in an operation completely separated from the moulding process, in order to subsequently be able to have a disc-form with a centrally oriented hole.

To continue, it is obvious that the technique shown and described here, is based on die-casting or compression moulding of a plastic material, which is made slightly viscous through heating, and through a reduction of temperature in the mould is allowed to solidify to a disc substrate.

EP-A1-0 540 843

Here is shown and described a process for producing optical discs. It is proposed that onto a substrate (3), made of silicone, quartz, glass or metal, is applied a photo-resistant in the shape of a layer (1) and through exposure to light, developing and etching, a punch or stamper (6) is obtained and thereby a duplication may be achieved of an information pattern for an optical disc substrate by using a plastic, curable by means of UV light, a polymerised plastic material which is also used in the present invention.

10 Account of the present inventionTechnical problems

Considering the circumstance that the technical deliberations one skilled in the relevant art must perform in order to be able to offer a solution to one or more technical problems posed are initially an insight into the measures and/or the sequence of measures that must be taken and a choice of the means required, and on the basis thereof, the subsequent technical problems should be relevant in arriving at the present invention.

Considering the earlier state of the art as described above, and utilising a method described more fully in the preamble to claim 1, and also an arrangement for producing plastic products described more fully in the preamble to claim 15, it should be deemed a technical problem to make use of the principles for the methods and the arrangement for producing plastic products described more fully in the above-mentioned publications, in order rationally, at lower cost and observing higher precision, to be able to create such conditions that a plastic product can be produced having microstructure-related surface portions of various types.

A technical problem exists, using simple measures, in being able to create such conditions that a viscous polymerisable plastic material can be supplied in a ring-shape to a cavity, such as around a hole pertaining to the finished plastic product, and that said viscous plastic material is distributed in a radial direction from said hole towards the peripheral edge area or areas of the plastic product.

A technical problem also exists, using simple measures, in being able to create conditions for producing a plastic product with surface portions assigned a

microstructure where the microstructure can be chosen fine for storing information and/or coarse for other technical applications, such as microfluids.

It should furthermore be considered a technical problem, using simple measures, to be able to create such conditions that the plastic product can be produced by die-casting or compression moulding.

A technical problem is also entailed in an application of this type, in being able to realise the significance of and advantages associated with being able to attach a substrate to one mould part, to which substrate the thin polymerisable plastic material shall adhere during the polymerisation.

A technical problem is also entailed in being able to realise the significance of and advantages associated with one of the substrate's or the insert's surfaces defining the cavity having a microstructure or alternatively being covered by a layer.

A technical problem is also entailed in being able to realise the significance of and advantages associated with one cavity-defining surface or an insert related thereto of a second mould part having a microstructure.

A technical problem is also entailed in being able to realise the significance of allowing said second cavity to have the shape and thickness of a CD disc, or thinner, or the like, said second cavity being defined by the insert by an outer concentric circular ring around the peripheral edge area.

A technical problem is also entailed in being able to realise the significance of and advantages associated with said substrate or insert forming an outer, annular ridge, the latter provided with narrow grooves.

A technical problem is also entailed in being able to realise the significance of and advantages associated with letting said outer ring delimit the distribution of the plastic material before polymerisation by means of measures entailing curing by means of light or the like.

A technical problem is also entailed in being able to realise the significance of said viscous plastic material being supplied to said cavity under positive pressure and by a circular valve arrangement.

A technical problem is also entailed in being able to realise the significance of and advantages associated with said first and second cavities being placed under negative pressure until the mould parts have been moved to said fully united position.

It would appear to be a technical problem, using simple measures, to be able to create such conditions that said cavity is placed under negative pressure, at least while the viscous plastic material is being injected.

5 Solution

In order to solve one or more of the technical problems listed above, the present invention commences from a method of producing a plastic product having at least one microstructured surface or surface portion, utilising an arrangement for producing plastic products.

10 This arrangement shall be provided with at least two mould parts movable towards and away from each other, a predetermined volume of a viscous polymerisable plastic material being supplied to a cavity formed between the mould parts and that, after said polymerisation of the plastic material, the mould parts are caused to move apart from each other to allow removal of a finished plastic
15 product the outer shape of which conforms to the inner shape of a cavity produced by the mould parts.

The invention specifies that said viscous polymerisable plastic material shall be supplied to a cavity around a hole pertaining to the finished plastic product, and that said viscous plastic material shall, through the displacement movement of the mould parts towards each other or similar, be distributed in a direction
20 from said hole towards the peripheral edge area of the plastic product.

Suggested embodiments falling within the scope of the present invention include that, if the plastic product is produced by means of die-casting, when said mould parts assume a fully united position the viscous polymerisable plastic material is pressed in within a central area of the finished plastic product and in
25 proximity to a hole allocated to the plastic product.

If the plastic product is produced by means of compression moulding, in an almost fully united position of the mould parts and a first cavity thus formed between the mould parts, a predetermined volume of a viscous polymerisable plastic material is supplied to said first cavity, after which the mould parts are
30 pressed together to a fully united position in order to distribute said plastic material within a second cavity the inner shape of which corresponds to the outer shape of the final plastic product, whereafter polymerisation of the plastic material occurs with the mould parts in a fully united position, then said viscous polym-

erisable plastic material shall be supplied to the first cavity within the central area of the finished plastic product and in proximity to a hole allocated to the plastic product.

Furthermore, it is proposed that, upon movement of the mould parts towards a fully united position, said viscous plastic material shall be distributed within the cavity in a direction from said hole and towards the peripheral edge area of the plastic product.

When producing a symmetrical disc the plastic material shall be supplied around a centrally located hole and the plastic material shall spread in radial direction.

Suggested embodiments falling within the scope of the present invention also include that an insert or a substrate may be attached to at least one of the mould parts, to which insert or substrate the polymerisable plastic material shall adheres after polymerisation.

Also proposed is that one of the substrate's surfaces defining the cavity may have a microstructure, preferably covered by a semi-reflecting layer.

Also proposed is for one cavity-defining surface (or insert) of a second mould part to be partially or entirely microstructured.

The invention also proposes that said second cavity be defined by an outer circular ring formed in an insert or in a substrate around a peripheral edge area before measures are taken to polymerise a plastic material enclosed in the second cavity.

Also proposed is for said substrate to be provided with an outer, annular ridge, the latter provided with narrow grooves.

Said outer circular ring may also be formed by means of surface-determined measures for curing by means of light or the like.

Said viscous plastic material shall be supplied to said first cavity under positive pressure and via a circular valve arrangement.

Said first cavity shall preferably be placed under negative pressure until and when the mould parts have been moved to said fully united position.

Advantages

The advantages that can be primarily considered significant for a method and an arrangement for producing plastic products in accordance with the inven-

tion are that conditions are thus created allowing a plastic material to be used which is not cured by adjusted temperature drops, to produce either discs with a fine microstructure and high storage capacity or discs with a coarse microstructure suitable for other applications in the microstructure field, such as microfluids.

5 The invention enables the use of a viscous plastic material with low temperature which gives good replication capability and where curing or polymerisation occurs through measures other than drops in temperature, such as by being subjected to the influence of light, e.g. UV light.

10 The present invention also enables the manufacture of discs for storing information, having high storage capacity, by offering at least two reflecting layers of microstructures where a first information surface must be semi-reflecting with a reflection factor of between 20 and 40%.

15 The principal features of a method in accordance with the present invention are defined in the characterizing part of the appended claim 1 and the principal features of an arrangement for producing plastic products in accordance with the invention are defined in the characterizing part of the appended claim 15.

Brief description of the drawings

20 The previous state of the art and a presently proposed arrangement for producing plastic products, illustrating the significant features necessary for performance of the method in accordance with the invention will now be described in more detail with reference to the accompanying drawings, in which:

Figure 1 shows a side view and generally an arrangement for producing plastic products, of a type known per se,

25 Figure 2 shows various sequences of the production of a plastic product by means of compression moulding in the arrangement shown in Fig. 1,

Figure 3 shows on a larger scale than in Figure 1, an assembly and co-operation between two used mould parts, in accordance with the invention,

30 Figure 4 shows on an enlarged scale a lower part for the assembly shown in Figure 3,

Figure 5 shows on an enlarged scale co-operation significant to the invention between two mould parts at the peripheral edge part of a produced disc,

- Figure 6 shows, on a somewhat larger scale than in Figure 3, a valve arrangement significant to the invention, for pressing out a viscous polymerisable plastic material, Figure 6 showing the valve in a closed position and the mould parts in fully united position,
- 5 Figure 7 shows the valve arrangement in an open position to enable a pre-determined volume of a viscous polymerisable plastic material to be pressed into a first space formed when the mould parts assume an almost fully united position to produce a first cavity,
- 10 Figure 8 shows the mould parts in a fully united position and with the pre-determined volume distributed within a second cavity and along the whole disc produced,
- Figure 9 shows on a somewhat enlarged scale the edge area of a substrate or an insert, provided with an outer annular ridge and a seal offering a negative pressure in the first and second cavities,
- 15 Figure 10 shows the possibility of forming an outer circular ring with the aid of light-curing measures,
- Figure 11 shows in perspective a disc produced in accordance with the invention,
- Figure 12 shows a section through a fine microstructure for a disc carrying information, such as a CD disc, and
- 20 Figure 13 shows a section through a disc provided with coarse microstructure suitable for microfluids.

Description of the state of the art

25 Figures 1 and 2 show schematically an arrangement for producing plastic products where the plastic product P formed has at least one surface with a microstructure.

The arrangement for producing plastic products has been designated 1.

30 The arrangement 1 is provided with at least two mould parts, an upper mould part 2 and a lower mould part 3, which are movable towards and away from each other with the aid of a first means 4.

The arrangement 1 is designed to be able to produce a plastic product with a microstructured outer surface, said arrangement having at least two mould parts movable in relation to each other, a cavity formed between the mould parts

being supplied with a predetermined volume of a viscous polymerisable plastic material.

After a polymerisation of the plastic material the mould parts are moved apart in order to allow removal of a finished plastic product, the outer shape of which conforms to the inner shape of the cavity formed by the mould parts.

The arrangement 1 can be used for die-casting or compression moulding and the latter application will be described in more detail.

In almost fully united position of these two mould parts 2, 3 a first cavity is formed between the mould parts, and a predetermined volume of a viscous polymerisable plastic material 9 is supplied to said first cavity 5. This is achieved by means of second means 7.

The mould parts 2 and 3 are pressed together by said first means 4 to a fully united position and, under positive pressure, said viscous plastic material 9 is distributed within a smaller second cavity 6.

The second cavity 6 corresponds to the shape of the final plastic product which, in the present application, consists of a disc such as a CD disc having one or more surfaces or surface portions provided with microstructure.

Polymerisation of the plastic material in the second cavity 6 occurs with the mould parts 2, 3 in fully united position, with the aid of a third means 8 in the form of a light-generating unit, such as a UV light generating unit.

After said polymerisation of the plastic material by subjection to the influence of light, the mould parts are caused by said first means 4 to move apart from each other, thereby allowing removal of a finished polymerised plastic product from the second cavity 6 formed by the mould parts.

Figure 2 illustrates in sequence the method of producing a plastic product with a microstructured surface according to the known method.

Description of a proposed embodiment

The invention now specifically states that said viscous polymerisable plastic material shall be supplied to the cavity around a hole pertaining to the finished plastic product, and that said viscous plastic material is distributed in a direction from said hole and towards the peripheral edge area of the plastic product.

It is also specified that when production of the plastic product is performed by means of die-casting said mould parts should assume a fully united position. In this position the viscous polymerisable plastic material is pressed into the central area for the finished plastic product in proximity of a hole pertaining to the finished plastic product.

When the plastic product is produced by means of compression moulding wherein, in almost fully united position of the mould parts a first cavity 5 is formed between the mould parts, a predetermined volume of a viscous polymerisable plastic material 9 is introduced to said first cavity, after which the mould parts are pressed together to a fully united position in order to distribute said plastic material 9 within a small, second cavity 6, the inner shape of which corresponds to the outer shape of the final plastic product, whereafter polymerisation of the plastic material occurs with the mould parts in fully united position, said viscous polymerisable plastic material shall be supplied to the first cavity within the central area of the finished plastic product and in proximity to a hole allocated to the plastic product.

Said viscous plastic material is distributed within the reduced volume of the cavity in a direction from said hole towards the peripheral edge area of the plastic product when the mould parts are moved towards a fully united position.

For production of a symmetrical disc it is proposed that the plastic material be supplied around a centrally placed hole and that the plastic material spreads in radial direction.

Figure 3 shows in side view and in section, two mould parts 2, 3 in the arrangement 1 for producing plastic products, these parts being shown in fully united position, thereby revealing the second cavity 6 which corresponds to the shape of the finished disc-shaped plastic product P.

Figure 7 shows a side view of the relative position between the mould parts 2, 3 upon the formation of said first cavity 5 therebetween.

Said viscous polymerisable material 9 shall be supplied via a second means 7 to the first cavity 5 around a centrally placed hole 10a, pertaining to the plastic product, in a produced multi-layered disc 10.

When the mould parts 2, 3 are moved by said first means 4 towards a fully united position, said viscous plastic material 9 shall be caused to spread

uniformly radially from said hole 10a towards the peripheral edge area 10b of the plastic product P.

Figure 4 shows how the second means 7, in the form of a pump and a volume- or pressure-regulating circuit, feeds viscous polymerisable plastic material (9) through a connection 12 and a tube 13 up to a valve 14 (shown in more detail in Figures 6, 7 and 8).

Figure 5 shows the left-hand peripheral edge area 10b in Figure 3 on a somewhat enlarged scale, from which it is clear that a viscous polymerisable plastic material 9 has been pressed out towards the edge of a flat substrate 15, manufactured previously and serving as an insert or a carrier, after the plastic material 9 has been polymerised to a hard disc 9'.

The disc 10 may thus (according to Figure 11) consist of a inserted substrate 15 with a surface 15a having a microstructure 15b, a semi-transparent or semi-reflecting thin layer 20, and a polymerised cured disc 9' produced through plastic moulding and having a microstructure 9a' and a reflecting layer 9b', produced in a separate station.

The transparent substrate 15 with the semi-reflecting layer 20 shall now, as an insert, be coated with a polymerisable hard transparent disc 9', with a microstructure 9a' formed by the second mould part.

Figure 6 shows in side view and in section an embodiment of a valve arrangement 14.

This shows how a central channel 13 communicates with a space 14a via one or more radially directed channels, one of which has been designated 13a.

Figure 6 shows, in an enlarged detail, that the space 14a is sealed against an edge 14b and the outer, surface of a cone 14c having the shape of a cylinder and a truncated cone.

Figure 6 also illustrates that the preformed substrate 15 made of plastic and having a microstructured surface 15a adhering to one mould part 2, against which substrate 15 and a layer 20 covering the surface 15a the polymerisable plastic material 9 is intended to adhere upon polymerisation to a hard disc 9'.

One cavity-defining surface 15a of the substrate 15 may be smooth but in the embodiment shown by way of example in Figure 6 this surface 15a is shown as having a microstructure 15b.

The cavity-defining surface 3a of the other mould part 3 is intended to have a microstructure 3b.

Although the drawings here show that the microstructure 3b is formed directly on the surface 3a of the second mould part 3, there is nothing to prevent an insert or a substrate corresponding to the substrate 15 from being applied on this surface 3a, the substrate being adhered against the surface 3a to the second mould part 3.

As previously mentioned said second cavity 6, in the shape of a CD-disc, is designed to be defined by a pin 14d inserted through the hole 10a, and an outer circular ring oriented at a peripheral edge area 10b, before measures are taken via a third means 8 for polymerisation of an enclosed plastic material.

An outer, annular ridge 15d provided with a plurality of outwardly directed grooves 15d' is applied on said substrate 15.

Said grooves 15d' may advantageously be radially oriented, but may also be arranged obliquely or in the shape of a labyrinth.

Figure 9 shows that the ridge 15d shall seal against the surface 3a and that, if the second cavity 6 is filled irregularly from the hole 10a, the plastic material 9 shall be prevented from flowing further. A number of grooves 15d' in the ridge 15d increases the resistance of the plastic material against flowing out, in favour of an easier flow-path via other channels.

The size and number of the grooves 15d' is a question of dimensioning, based on the relevant application and plastic material selected.

Figure 10 shows that an outer circular ring 9d may be formed by means of light-curing measures or the like.

Figure 10 shows that a mask 30 is placed centrally over the substrate 15 and, via a line 15e, shadows a considerable part of the plastic material 9 of the disc 10 but illuminates a circular ring-shaped part 9d, before the material 9 of the disc 10 is polymerised to 9'.

When the plastic material 9 is pressed out to the part 9d, it is polymerised and forms a constriction or ridge that prevents further passage of plastic material 9 with a distribution of the plastic material 9 within the second cavity 6.

The mask 30 can then be removed so that the rest of the plastic material 9 can be subjected to polymerisation to a hard disc 9'.

Said viscous plastic material 9 is intended to be able to be supplied via second means 7 to said first cavity 5 under suitable positive pressure and via a circular valve arrangement 14.

5 Said first cavity is placed under negative pressure by a fourth means during the time while the mould parts are being moved to said fully united position.

Figure 9 illustrates how cavities 5 and 6, respectively, are sealed by a sealing ring 40 when a negative pressure prevails.

10 Figure 11 shows in perspective a disc 10 produced in accordance with the present invention, from a substrate 15 with a downwardly facing surface 15a assigned a microstructure 15b, and covered by a semi-reflecting layer 20.

This microstructure 15a is now reproduced in mirror-inversion on a surface of the polymerised layer 9', which has a microstructure 9a' on its surface 9a corresponding to microstructures for the surface 3a.

15 The surface 9a belonging to the microstructure 9a' may advantageously be covered with a reflecting layer 9b'.

In accordance with the invention and Figure 12, the disc 10 can be given a fine micro-structure 10f with the layer 9b', thereby making the disc 10 suitable for storing information, such as a CD-disc in accordance with Figure 11.

20 In accordance with the invention the disc 10 can be given a coarse, channelled microstructure 10e. Figure 13 illustrates an application in which the disc 10 rests on a carrier 130 and seals a channel 131.

A fluid 132 flows through channels 131 and the fluid 132 can be analysed via laser beams 133 or the like through the disc 10.

25 The invention is naturally not limited to the embodiment described above by way of example. Modifications are possible within the scope of the inventive concept illustrated in the appended claims.

CLAIMS

1. A method of producing a plastic product having a microstructured outer surface, utilising an arrangement for moulding plastic products, said arrangement
5 having at least two mould parts movable towards and away from each other, a predetermined volume of a viscous polymerisable plastic material being supplied to a cavity formed between the mould parts, after which polymerisation of the plastic material occurs and, after said polymerisation of the plastic material, the
10 mould parts being caused to move apart from each other to allow removal of a finished plastic product the outer shape of which conforms to the inner shape of the cavity produced by the mould parts, **characterized** in that said viscous polymerisable plastic material is supplied to the cavity around a hole pertaining to the finished plastic product, and in that said viscous plastic material shall be distributed in a direction from said hole towards the peripheral edge area of the plastic
15 product.
2. A method as claimed in claim 1 wherein the plastic product is produced by means of die-casting, **characterized** in that when said mould parts assume a fully united position the viscous polymerisable plastic material is pressed in within
20 a central area of the finished plastic product and in proximity to a hole allocated to the plastic product.
3. A method as claimed in claim 1 wherein the plastic product is produced by means of compression moulding where, in an almost fully united position of the
25 mould parts and a first cavity thus formed between the mould parts, a predetermined volume of a viscous polymerisable plastic material is supplied to said first cavity, after which the mould parts are compressed to a fully united position in order to distribute said plastic material within a smaller second cavity, the inner shape of which corresponds to the outer shape of the final plastic product,
30 whereafter polymerisation of the plastic material occurs with the mould parts in a fully united position, **characterized** in that said viscous polymerisable plastic material is supplied to the first cavity within the central area of the finished plastic product and in proximity to a hole allocated to the plastic product.

4. A method as claimed in claim 3, **characterized** in that upon movement of the mould parts towards a fully united position, said viscous plastic material is distributed within the cavity in a direction from said hole and towards the peripheral edge area of the plastic product.

5

5. A method as claimed in claim 1 for producing a symmetrical disc, **characterized** in that the plastic material is supplied around a centrally located hole and in that the plastic material spreads in radial direction.

10

6. A method as claimed in claim 1, **characterized** in that a substrate is attached as an insert to one of the mould parts, to which substrate the polymerisable plastic material adheres.

15

7. A method as claimed in claim 1 or claim 6, **characterized** in that one of the substrate's surfaces defining the cavity has a microstructure, covered by a semi-reflecting layer.

20

8. A method as claimed in claim 1, **characterized** in that one cavity-defining insert or surface of a second mould part has a microstructure.

25

9. A method as claimed in claim 3, **characterized** in that said second cavity with an inner shape conforming to an outer shape of a disc or the like, is defined by an outer circular ring oriented at a peripheral edge area before measures are taken to polymerise a plastic material enclosed.

30

10. A method as claimed in claim 6, **characterized** in that said substrate is provided with an outer, annular ridge provided with narrow grooves.

11. A method as claimed in claim 9, **characterized** in that said outer ring is formed by means of light-curing measures or the like.

12. A method as claimed in claim 1 or claim 3, **characterized** in that said viscous plastic material is supplied to the cavity under pressure and via a circular valve arrangement.

5 13. A method as claimed in claim 3, **characterized** in that said first and second cavities are placed under a negative pressure until the mould parts have been moved to said fully united position.

10 14. A method as claimed in claim 1 or claim 2, **characterized** in that said cavity is placed under a negative pressure while the viscous plastic material is being injected.

15 15. An arrangement for moulding plastic products in which the plastic product produced has at least one surface with a microstructure, said arrangement having at least two mould parts movable towards and away from each other by a first means, a predetermined volume of a viscous polymerisable plastic material being supplied to a cavity formed between the mould parts, after which polymerisation of the plastic material occurs and, after said polymerisation of the plastic material, the mould parts being caused by said means to move apart from each other
20 thereby allowing removal of a finished plastic product, the outer shape of which conforms to the inner shape of the cavity produced by the mould parts, **characterized** in that said viscous polymerisable plastic material, via a second means, can be supplied to the cavity around a hole allocated to the finished plastic product and in that said viscous plastic material is caused to be distributed in a direction from said hole towards the peripheral edge area of the plastic product.
25

16. An arrangement as claimed in claim 15 where the plastic product is produced by means of die-casting, **characterized** in that when said mould parts are caused by said first means to assume a fully united position, the viscous polymerisable plastic material is injected within the central area for the finished plastic product and in proximity to a hole allocated to the plastic product.
30

17. An arrangement as claimed in 15 where the plastic product is produced by means of compression moulding wherein, in almost fully united position of the mould parts by means of said first means and a first cavity formed between the mould parts, a predetermined volume of a viscous polymerisable plastic material is introduced to said first cavity, after which said mould parts are pressed together by said first means to a fully united position in order to distribute said plastic material within a small, second cavity, the inner shape of which corresponds to the outer shape of the final plastic product, whereafter polymerisation of the plastic material occurs with the mould parts in fully united position, **characterized** in that said viscous polymerisable plastic material is arranged to be supplied to the first cavity within the central area of the finished plastic product and in proximity to a hole allocated to the plastic product.

18. An arrangement as claimed in claim 17, **characterized** in that said viscous plastic material is arranged to be distributed within the cavity in a direction from said hole towards the peripheral edge area of the plastic product when the mould parts are moved towards a fully united position.

19. An arrangement as claimed in claim 15 for producing a symmetrical disc, **characterized** in that the plastic material is supplied to a centrally placed hole and that the plastic material spreads in radial direction.

20. An arrangement as claimed in claim 15, **characterized** in that a substrate of plastic is attached to one of the mould parts, to which substrate the polymerisable plastic material is designed to adhere.

21. An arrangement as claimed in claim 15 or claim 20, **characterized** in that one cavity-defining surface of the substrate is provided with a microstructure, covered by a semi-reflecting layer.

22. An arrangement as claimed in claim 15, **characterized** in that one cavity-defining surface of a second mould part has a microstructure.

23. An arrangement as claimed in claim 15, **characterized** in that said second cavity with an inner shape conforming to the outer shape of a disc or the like, is designed to be defined by an outer circular ring oriented at the peripheral edge area before measures are taken, via a third means, for polymerisation of a plastic material enclosed.

24. An arrangement as claimed in claim 15, **characterized** in that to said substrate or insert is applied an outer, annular ridge, the latter being provided with a plurality of narrow grooves.

25. An arrangement as claimed in claim 23, **characterized** in that said outer circular ring is designed to be formed by means of light-curing measures or the like.

26. An arrangement as claimed in claim 15, **characterized** in that said viscous plastic material is designed, via second means, to be supplied to said cavity under a suitable positive pressure and via a circular valve arrangement.

27. An arrangement as claimed in claim 17, **characterized** in that said first and second cavities are, by means of a fourth means, placed under a negative pressure until the mould parts have been moved to said fully united position.

28. An arrangement as claimed in claim 15 or claim 16, **characterized** in that said cavity is placed under a negative pressure while the viscous plastic material is being injected.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
1 March 2001 (01.03.2001)


PCT

(10) International Publication Number
WO 01/14116 A1

- (51) International Patent Classification⁷: B29C 33/42 // B29L 17:00
- (74) Agents: JOHANSSON WEBJÖRN, Ingmari et al.; L.A. Groth & Co. KB, Box 6107, S-102 32 Stockholm (SE).
- (21) International Application Number: PCT/SE00/01649
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AT (utility model), AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, CZ (utility model), DE, DE (utility model), DK, DK (utility model), DM, DZ, EE, EE (utility model), ES, FI, FI (utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (utility model), SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (22) International Filing Date: 28 August 2000 (28.08.2000)
- (25) Filing Language: Swedish
- (26) Publication Language: English
- (30) Priority Data:
9903011-6 26 August 1999 (26.08.1999) SE
- (71) Applicant (*for all designated States except US*): ÅMIC AB [SE/SE]; Uppsala Science Park, S-751 83 Uppsala (SE).
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): ÖHMAN, Per, Ove [SE/SE]; Asplunda Uppsala-Näs, S-755 91 Uppsala (SE). LUNDBLADH, Lars, Rune [SE/SE]; Gökärtsvägen 63, S-187 51 Täby (SE).
- Published:
— With international search report.

[Continued on next page]

(54) Title: A METHOD OF PRODUCING A PLASTIC PRODUCT AND AN ARRANGEMENT FOR MOULDING PLASTIC PRODUCTS UTILISED THEREFOR



(57) Abstract: A method of producing a plastic product having a microstructured surface (3a), utilising an arrangement for moulding plastic products. Said arrangement has at least two mould parts (2, 3) movable towards and away from each other, a predetermined volume of a viscous polymerisable plastic material (9) being supplied to a cavity formed between the mould parts, after which polymerisation of the plastic material occurs. After said polymerisation of the plastic material (9'), the mould parts are caused to move apart from each other thereby allowing removal of a finished plastic product the outer shape of which conforms to the shape of the cavity produced by the mould parts. Said viscous polymerisable plastic material (9) is supplied to the cavity (6) around a hole (10a) pertaining to the finished plastic product, and said viscous plastic material is distributed in a direction from said hole (10a) towards the peripheral edge area of the plastic product.




Fig. 1.




Fig. 2.




Fig. 3




Fig. 4




Fig. 5




Fig. 6




Fig. 7




Fig. 8




Fig. 9




Fig. 10




Fig. 11




Fig. 12.




Fig. 13.

BIRCH, STEWART, KOLASCH & BIRCH, LLP

P.O. Box 747 • Falls Church, Virginia 22040-0747
 Telephone: (703) 205-8000 • Facsimile: (703) 205-8050

PLEASE NOTE:
 YOU MUST
 COMPLETE THE
 FOLLOWING

COMBINED DECLARATION AND POWER OF ATTORNEY FOR PATENT AND DESIGN APPLICATIONS

As a below named inventor, I hereby declare that: my residence, post office address and citizenship are as stated next to my name; that I verily believe that I am the original, first and sole inventor (if only one inventor is named below) or an original, first and joint inventor (if plural inventors are named below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

Insert Title: A METHOD OF PRODUCING A PLASTIC PRODUCT AND AN ARRANGEMENT FOR MOULDING PLASTIC PRODUCTS
UTILISED THEREFOR

Fill in Appropriate Information - For Use Without Specification Attached: the specification of which is attached hereto. If not attached hereto, the specification was filed on _____ as United States Application Number _____; and amended on _____ (if applicable) and/or _____ as PCT International Application Number PCT/SE00/01649; and was amended on _____ (if applicable)

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, §1.56.

I do not know and do not believe the same was ever known or used in the United States of America before my or our invention thereof, or patented or described in any printed publication in any country before my or our invention thereof or more than one year prior to this application, that the same was not in public use or on sale in the United States of America more than one year prior to this application, that the invention has not been patented or made the subject of an inventor's certificate issued before the date of this application in any country foreign to the United States of America on an application filed by me or my legal representative or assigns more than twelve months (six months for designs) prior to this application, and that no application for patent or inventor's certificate on this invention has been filed in any country foreign to the United States of America prior to this application by me or my legal representatives or assigns, except as follows.

I hereby claim foreign priority benefits under Title 35, United States Code, §119(a)-(d) of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

Insert Priority Information: (if appropriate)	Prior Foreign Application(s)			Priority Claimed	
	<u>9903011-6</u> (Number)	<u>Sweden</u> (Country)	<u>August 26, 1999</u> (Month/Day/Year Filed)	<input checked="" type="checkbox"/> Yes	<input type="checkbox"/> No
	<u> </u> (Number)	<u> </u> (Country)	<u> </u> (Month/Day/Year Filed)	<input type="checkbox"/> Yes	<input type="checkbox"/> No
	<u> </u> (Number)	<u> </u> (Country)	<u> </u> (Month/Day/Year Filed)	<input type="checkbox"/> Yes	<input type="checkbox"/> No
	<u> </u> (Number)	<u> </u> (Country)	<u> </u> (Month/Day/Year Filed)	<input type="checkbox"/> Yes	<input type="checkbox"/> No

I hereby claim the benefit under Title 35, United States Code, §119(e) of any United States provisional applications(s) listed below.

Insert Provisional Application(s): (if any)	(Application Number)	(Filing Date)
	<u> </u>	<u> </u>
	<u> </u>	<u> </u>

All Foreign Applications, if any, for any Patent or Inventor's Certificate Filed More than 12 Months (6 Months for Designs) Prior to the Filing Date of This Application:

Insert Requested Information: (if appropriate)	Country	Application Number	Date of Filing (Month/Day/Year)
	<u> </u>	<u> </u>	<u> </u>
	<u> </u>	<u> </u>	<u> </u>

I hereby claim the benefit under Title 35, United States Code, §120 of any United States and/or PCT application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States and/or PCT application in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose information which is material to the patentability as defined in Title 37, Code of Federal Regulations, §1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application.

Insert Prior U.S. Application(s): (if any)	(Application Number)	(Filing Date)	(Status - patented, pending, abandoned)
	<u> </u>	<u> </u>	<u> </u>
	<u> </u>	<u> </u>	<u> </u>

I hereby appoint the practitioners at **CUSTOMER NO. 2292** as my attorneys or agents to prosecute this application and/or an international application based on this application and to transact all business in the United States Patent and Trademark Office connected therewith and in connection with the resulting patent based on instructions received from the entity who first sent the application papers to the practitioners, unless the inventor(s) or assignee provides said practitioners with a written notice to the contrary:

Send Correspondence to:

BIRCH, STEWART, KOLASCH & BIRCH, LLP or **CUSTOMER NO. 2292**

P.O. Box 747 • Falls Church, Virginia 22040-0747

Telephone: (703) 205-8000 • Facsimile: (703) 205-8050

PLEASE NOTE:
YOU MUST
COMPLETE
THE
FOLLOWING:

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon

Full Name of First
or Sole Inventor;
Insert Name of
Inventor
Insert Date This
Document is Signed

Insert Residence
Insert Citizenship

Insert Post Office
Address

Full Name of Second
Inventor, if any;
see above

Full Name of Third
Inventor, if any;
see above

Full Name of Fourth
Inventor, if any;
see above

Full Name of Fifth
Inventor, if any;
see above

Full Name of Sixth
Inventor, if any;
see above

GIVEN NAME/FAMILY NAME	INVENTOR'S SIGNATURE	DATE*
Per Ove OHMAN	<i>Per Ove Ohman</i>	08 FEB. 2002
Residence (City, State & Country)	CITIZENSHIP	
Uppsala SWEDEN SEX	Swedish	
MAILING ADDRESS (Complete Street Address including City, State & Country)		
Asplunda Uppsala-Nas, S-755 91 Uppsala SWEDEN		
GIVEN NAME/FAMILY NAME	INVENTOR'S SIGNATURE	DATE*
Lars Rune LUNDBLADH	<i>Lars Rune Lundblad</i>	08 FEB. 2002
Residence (City, State & Country)	CITIZENSHIP	
Taby SWEDEN SEX	Swedish	
MAILING ADDRESS (Complete Street Address including City, State & Country)		
Gokartsvagen 63, S-187 51 Taby SWEDEN		
GIVEN NAME/FAMILY NAME	INVENTOR'S SIGNATURE	DATE*
Residence (City, State & Country)	CITIZENSHIP	
MAILING ADDRESS (Complete Street Address including City, State & Country)		
GIVEN NAME/FAMILY NAME	INVENTOR'S SIGNATURE	DATE*
Residence (City, State & Country)	CITIZENSHIP	
MAILING ADDRESS (Complete Street Address including City, State & Country)		
GIVEN NAME/FAMILY NAME	INVENTOR'S SIGNATURE	DATE*
Residence (City, State & Country)	CITIZENSHIP	
MAILING ADDRESS (Complete Street Address including City, State & Country)		
GIVEN NAME/FAMILY NAME	INVENTOR'S SIGNATURE	DATE*
Residence (City, State & Country)	CITIZENSHIP	
MAILING ADDRESS (Complete Street Address including City, State & Country)		